

Micron[®] CSC - CA

Multi-season antifouling for all fouling conditions

Micron CSC – CA is a multi-season antifouling paint based on Controlled Solubility Copolymer technology. This product is designed to wear away (polish) at a controlled rate providing multi-season protection with reduced paint buildup allowing for an easier reapplication and improved performance. It will provide excellent multi-season longevity against all types of algae, weeds, barnacles, and other shell fouling. Micron CSC – CA can be used below the waterline in fresh, salt or brackish water on fiberglass, wood and properly primed metal boat hull and parts. Do not use on aluminum.

Product Features

- Premium multi-season performance
- High solids formulation
- Can be applied down to 5°C / 41°F
- Compatible over most antifouling
- Suitable for power and sail, in all waters

Product Data

Color and code	Blue YBM000, Red YBM002, Black YBM003
Coverage	By brush and roller: 505.2 ft ² /gal.
Surfaces	Fiberglass, wood and properly primed metals. Do not use on small aluminum boats. For large aluminum boats, contact Interlux Technical Service
Dry times at 73°F (23°C)	Touch Dry: 4 hrs Time to Immersion: 8 hrs
Application method	Brush, Roller
Application temperature	41°F (5°C) to 95°F (35°C)
Coats required	2-3
VOC	385 grams/ltr as supplied
Case pack	2 gallons per case



Associated Products

Fiberglass Surface Prep YMA601V

Water based cleaner for bare fiberglass

Watertite YAV135

Epoxy filling and fairing compound

InterProtect[®] 2000E

Universal epoxy primer for above and below the waterline



Blue YBM000

Red YBM002

Black YBM003

Recommended Application Systems – General Directions

Surface Preparation

Shake or mix well prior to use. Apply at least 2 full coats (3 coats on bare wood) of Micron CSC – CA by brush or solvent resistant 3/8" nap roller. Do not apply thin coats. Keep in mind that the life of the paint is directly related to the amount of paint applied. If during application, brush pulls or roller drags, use Special Thinner 216 to improve handling. Certain areas of hull experience faster polishing than other areas. These areas include the waterline, the leading edge of the keel and rudder, and the bow stem. On these areas, it is suggested that an additional coat of paint be applied to ensure that Micron CSC – CA does not wash away before the other areas of the bottom.

Previously Painted Surfaces – Good Condition:

Remove all traces of loose paint and contamination by sanding the entire surface well with 80 grit wet or dry sandpaper; wipe surface clean with Special Thinner 216. Apply at least 2 coats of Micron CSC – CA allowing proper dry times.

Previously Painted Surfaces – Poor Condition:

Completely remove all old antifouling paint with fiberglass-safe paint stripper or by blasting media for fiberglass and wood and by sandblasting steel surfaces to a near white metal. Proceed with application system for bare work as described below.

Bare fiberglass:

Begin by scrubbing the surface thoroughly with a stiff brush using soap and water to remove loose dirt and contamination. Flush with fresh water to remove the soap residue and allow to dry. Remove mold release wax using one of the following methods:

Low VOC System:

Apply Fiberglass Surface Prep YMA601V with a maroon, 3M® Scotch-Brite™ pad and scrub well. Flush with fresh water or wipe off with a clean, wet cloth ensuring that no traces of Fiberglass Surface Prep YMA601V remain.

Application

Bare fiberglass – No Sand System:

After the surface has been prepared as described above repair any imperfections with Interlux Watertite™ YAV135 sand and wipe clean – apply one continuous coat of Interlux InterProtect 2000E. Please refer to label directions for application. Apply two coats minimum of Micron CSC – CA.

Bare fiberglass – Sanding System:

After the surface has been prepared as described above repair any imperfections with Watertite YAV135– Sand entire surface well with 80-grit sandpaper until flat matte finish is obtained. Remember to change sandpaper frequently. Wipe off sanding residue with Fiberglass Solvent Wash 202. Apply two coats minimum of Micron CSC – CA.

Bare wood:

Sand entire surface thoroughly with 80 grit production sandpaper; wipe surface clean with Special Thinner 216. Repair imperfections with Watertite YAV135; sand and wipe clean. Apply first coat of Micron CSC – CA reduced with Special Thinner 216 (10% maximum). Fill seams with seam compound between first and second coats of Micron CSC – CA.

Underwater Metals:

Contact the INTERLUX Technical Service Department at 1-800-468-7589 for full details on how to properly prime underwater metals. Do not use on aluminum.

Note: This product may change color at the waterline.

For technical assistance please contact the Interlux Technical Service Department at 1-800-468-7589 or visit interlux.com for additional product information.

International Paint LLC.

6001 Antoine Dr., Houston, TX USA 77091

Tel: (713) 682-1711 Technical Support Tel: 1-800-468-7589 Email: InterluxTechnicalService@akzonobel.com

The information given in this sheet is not intended to be exhaustive. Any person using this product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous development. Please refer to your local representative or interlux.com for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

© AkzoNobel 2021

9755/0221
YAT076